

In the claims:

Claims 1 to 10 canceled.

11. (previously presented) A method of making a stator of an electric machine, said method comprising:

- a) making individual generally strip-shaped laminas (15) for the stator;
- b) stacking the individual laminas (15) to form a stator core (13) with a yoke (26) having a yoke height (H_{yoke}), so that one side of the stator core is provided with grooves (18) extending through the core;
- c) producing a subassembly by inserting a stator winding (17) into the grooves (18) of the stator core (13) formed in step b);
- d) bending the subassembly in a circular fashion to form a cylindrical cavity, so that the grooves (18) end in the cavity; and
- e) in order to keep the subassembly in a configuration with the cylindrical cavity, connecting at least two ends (23) of the stator core (13) to each other by means of a welding seam (20);
- f) selecting a depth of the welding seam to give the welding seam a sufficient strength to absorb tensile forces occurring in the welding seam, but at the same time not to exert too excessive a negative influence on magnetic properties at a welding point due to structural changes occurring in the yoke, said selecting including selecting a welding seam depth (T_s) of the welding seam (20)

is as a function of the yoke height (H_{yoke}) and a tolerance value (ΔT_S) in accordance with the following formula (I):

$$T_S = 0.5 \text{ mm} * (H_{yoke}/\text{mm} - 1) \pm \Delta T_S \quad (I); \text{ and}$$

selecting the welding seam depth (T_S) of the welding seam (20) to be not less than a minimum value (T_{Smin}) and said minimum value (T_{Smin}) to be dependent on the yoke height (H_{yoke}) and to be described by the following formula (II): $T_{Smin} = \{3/40\} * H_{yoke}$

12. (previously presented) The method as defined in claim 11, further comprising selecting the tolerance value (ΔT_S) to be 1.0 mm.

13. (previously presented) The method as defined in claim 11, further comprising selecting the tolerance value (ΔT_S) to be 0.5 mm.

Claim 14 cancelled.

15. (previously presented) The method as claimed in claim 11, further comprising arranging the welding seam (20) on a radial outside (30) of the yoke (26).

16. (previously presented) The method as claimed in claim 11, further comprising providing the stator core (13) with a plurality of teeth (25), arranging the welding seam (20) on a radial outside (30) of the yoke (26) and

arranging the welding seam (20) in one of said teeth, with said one of said teeth comprising two partial teeth (24).

17. (previously presented) The method as claimed in claim 11, further comprising disposing the welding seam (20) on at least one axial end of the stator core (13).

18. (previously presented) The method as claimed in claim 11, further comprising making the welding seam by a laser welding process with a laser beam.

Claims 19-23 cancelled.